

CI/SfB	Yu4	(K2)
CAW G12		
Uniclass JM61:L68116		

Product Information

Description

SC802 Intumescent Basecoat is a water-based, white, thin film intumescent coating for the protection of internal structural steelwork.

Usage / Purpose

SC802 is optimised to provide 60 minutes fire resistance to 'I' section beams and columns, hollow columns and beams, as well as cellular beams.

Finish

SC802 can be applied to a smooth matt finish. A compatible top-seal can be applied if a decorative finish is required.

Colour

White

Packaging

Supplied in 25 kg drums

Environmental Considerations

Very low VOC. Contains no substances of very high concern.

Availability

Only available via Nullifire Specialist Contractors or direct from Tremco CPG UK Limited (see details on this TDS).

Usage Guidelines

Protective Equipment

Use in well ventilated conditions and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

Surface Preparation & Priming

- SC802 should be applied onto a clean, undamaged and dry primed surface.
- Nullifire recommended primers are listed on the ETA and Nullifire's website
- Nullifire have carried out compatibility testing on a wide range of primers and topcoats and can be contacted on +44 (0)1322 551010 for confirmation of compatibility with SC802.
- The primer must be applied in accordance with the manufacturer's instructions.

Application Conditions

- Nullifire SC802 is recommended for application and use on dry protected structural steel only.
- If the basecoat is allowed to get wet, it is likely to be damaged – blistering and wrinkling may occur.
- SC802 should only be applied when the air and steel temperatures are above 5°C. Relative humidity should be below 80% for successful application. Steel surface temperature should be a minimum of 3°C above the dew point.
- Ensure the steel is dry and free from contact with rain or condensation during the application and drying of SC802.

Application Equipment

Airless spray equipment is recommended and should match these guidelines:

Operating Pressure: 2500- 3000psi (175 - 210 kg/cm²)

Tip Size: 17 – 21 thou

Fan Angle: 20° – 40°

Hose Diameter: 10 mm (3/8") (internal diameter)

Hose Length: Max. 60 metres, in-line filters should not normally be used.

Mixing

SC802 is supplied ready for use and must not be thinned but should be mechanically stirred prior to use.

Application

AIRLESS SPRAYING

- SC802 may be applied up to a maximum wet film thickness (WFT) of 1.0 mm in a single spray coat comprising of several quick passes. Achieving maximum loadings will depend on site conditions.
- The vast majority of 60 minute loadings can be applied in one coat.

BRUSH/ROLLER APPLICATION

- For brush application use a "laying on" technique to avoid heavy brush marking.
- Maximum wet film per coat when applied using a brush or roller is 0.6 mm. A short piled roller will produce a light textured finish.
- During application, measure the wet film thickness frequently with the WFT gauge provided to ensure the correct thickness is being applied.

Nullifire
Smart Protection

SC802

Intumescent Basecoat

On-Site, Water-Based



Key Benefits Summary

- Water based intumescent coating suitable for internal use on structural steelwork for up to 60 minute fire resistance
- "Next generation" product - with greater efficiency on site
- Compatible with a full range of Nullifire primers and top seals
- Very low VOC
- Optifire®+ unique traceability identifier

 **certifire**
APPROVAL N° CF5420



SC802

Intumescent Basecoat



- To use the gauge, insert the teeth into the wet basecoat. The last tooth to be coated indicates the wet film thickness achieved.
- In the event of over or under applications, adjustments to the loading rates of subsequent coats will be required.

Drying Times

WFT	Temperature		
	10°C	20°C	30°C
0.2 mm	3 h	2 h	1 h
0.5 mm	4 h	3 h	2 h
1.0 mm	6 h	4 h	3 h

These are times for a typical mid-range humidity and good air flow. Higher humidity, poor airflow or overnight condensation will all lengthen these times.

Do not over coat if the surface is not touch dry. Check web-flange joints.

Application Advice

The following instructions are for on-site application only. For off-site application, refer to Nullifire. Ensure that:

- The primer is compatible with SC802 and has been applied correctly.
- The overcoating period for the primer has not been exceeded.
- The correct primer is used for galvanised steel.
- All damage to the primer has been repaired & re-primed.
- Site and weather conditions are within specification.
- SC802 has been stored correctly.
- Surface is clean, dry and free from contamination.
- Correct spray equipment is available, if appropriate.
- Application instructions have been read prior to commencement of work.
- Ensure different basecoats are not applied on the same section of steel.
- Equipment should be clean and free from contaminants or dried material.
- Wet film gauges are available for use.

Cleaning

Spray equipment can be cleaned using water only.

Technical Data

Property	Result
Composition	A very low VOC, water-based formulation
Certification	BS476 Part 20/21, Certifire CF5420, Cellular Beams YB5 (for other certification requirements, contact Nullifire)
Building Classification	C1, C2 and C3 environments, For full details, please consult Nullifire Specification Guidelines.
Properties (Typical Values)	
Specific Gravity	1.38 ±0.02
Volume Solids	70% ±3%
VOC	≤16 g/l
Theoretical Coverage	979 g/m ² based on an applied 0.5 mm dry film thickness
Storage	Store in secure, dry warehouse conditions between +5°C and +35°C
Shelf Life (at +20°C)	9 months when stored as recommended in original unopened container

Top Seal Requirements

Once DFT's have been achieved as specified, a Nullifire top seal can be applied. Ensure the SC802 is completely dry before applying top seal. For approved top seals, please consult Nullifire's Approved Topcoat List.

Maintenance & Repair

Damaged areas should be abraded back to a sound surface. The surface should then be clean and dry before re-applying. FC101 Filler may be used for repairing scratches and chips. Once repaired topseal should be re-applied. Refer to Nullifire Maintenance Instructions.

Specification

A Tremco CPG UK Limited Representative will provide a specification for each project. Tremco CPG UK Limited accepts no responsibility for defects arising from failure to follow the specification.

Health & Safety Precautions

Safety data sheet must be read and understood before use.

Technical Service

Tremco CPG UK Limited has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on +44 (0)1322 551010.

Guarantee / Warranty

Tremco CPG UK Limited products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG UK Limited written instructions and (b) in any application recommended by Tremco CPG UK Limited, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct. Tremco CPG UK Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.